

## 9 . ステンレス鋼板重量表

A比重 7.70 SUS-430 表面積 4' × 8' 2,972  
 B比重 7.93 SUS-304 4' × 10' 3,716  
 C比重 7.98 SUS-316 316L 5' × 10' 4,645

表 9 - 1

( 単位 : kg )

	1,000×2,000			1,000×3,000			1,219×2,438 ( 4'×8' )			1,219×3,048 ( 4'×10' )			1,524×3,048 ( 5'×10' )	
	A	B	C	A	B	C	A	B	C	A	B	C	B	C
0.3	4.62	4.76	4.79	6.93	7.14	7.18	6.86	7.07	7.12	8.58	8.84	8.89		
0.4	6.16	6.34	6.38	9.24	9.52	9.58	9.15	9.43	9.49	11.4	11.8	11.9		
0.5	7.70	7.93	7.98	11.6	11.9	12.0	11.4	11.8	11.9	14.3	14.7	14.8		
0.6	9.24	9.52	9.58	13.9	14.3	14.4	13.7	14.1	14.2	17.2	17.7	17.8		
0.7	10.8	11.1	11.2	16.2	16.7	16.8	16.0	16.5	16.6	20.0	20.6	20.8		
0.8	12.3	12.7	12.8	18.5	19.0	19.2	18.3	18.9	19.0	22.9	23.6	23.7	29.5	29.6
0.9	13.9	14.3	14.4	20.8	21.4	21.5	20.6	21.2	21.3	25.8	26.5	26.7	33.2	33.4
1.0	15.4	15.9	16.0	23.1	23.8	23.9	22.9	23.6	23.7	28.6	29.5	29.7	36.8	37.1
1.2	18.5	19.0	19.2	27.7	28.5	28.7	27.5	28.3	28.5	34.3	35.4	35.6	44.2	44.5
1.5	23.1	23.8	23.9	34.7	35.7	35.9	34.3	35.4	35.6	42.9	44.2	44.5	55.3	55.6
2.0	30.8	31.7	31.9	46.2	47.6	47.9	45.8	47.1	47.4	57.2	58.9	59.3	73.7	74.1
2.5	38.5	39.7	39.9	57.8	59.5	59.8	57.2	58.9	59.3	71.5	73.7	74.1	92.1	92.7
3.0	46.2	47.6	47.9	69.3	71.4	71.8	68.6	70.7	71.2	85.8	88.4	89	111	111
3.5	53.9	55.5	55.9	80.8	83.3	83.8	80.1	82.5	83	100	103	104	129	130
4.0	61.6	63.4	63.8	92.4	95.2	95.8	91.5	94.3	94.9	114	118	119	147	148
5.0	77	79.3	79.8	116	119	120	114	118	119	143	147	148	184	185
6.0	92.4	95.2	95.8	139	143	144	137	141	142	172	177	178	221	222
8.0	123	127	128	185	190	192	183	189	190	229	236	237	295	297
10.0	154	159	160	231	238	239	229	236	237	286	295	297	368	371
12.0	185	190	192	277	285	287	275	283	285	343	354	356	442	445
15.0	231	238	239	346	357	359	343	354	356	429	442	445	553	556
16.0	246	254	255	370	381	383	366	377	380	458	471	474	589	593
18.0	277	285	287	416	428	431	412	424	427	515	530	534	663	667
20.0	308	317	319	462	476	479	458	471	474	572	589	593	737	741

備考 2.0厚み以上の熱間圧延鋼板重量は、板厚許容差JISG4304による記号Aで算出